

SIGRABOND® Sinter

Material: Carbon fiber-reinforced carbon (C/C)

Application: High-temperature applications especially for sintering processes

Material data of SIGRABOND® Sinter

Typical properties	Units	Sinter
Density	g/cm ³	1.45
Flexural strength	MPa	130
Flexural modulus	GPa	60
Tensile strength	MPa	150

Values without tolerance represent typical average values. For any engineering/design purposes please always contact our technical sales team.



Graphite Solutions | SGL CARBON GmbH
Sales Europe/Middle East/Africa | cfrc-europe@sglcarbon.com
Sales Americas | cfrc-americas@sglcarbon.com
Sales Asia/Pacific | cfrc-asia@sglcarbon.com
www.cfrc-and-felts.com | www.sglcarbon.com

TDS CFRC-T.00

07 2021/0 1NÄ Printed in Germany

®registered trademarks of SGL Carbon SE

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our "General Conditions of Sale".