

SIGRAFINE® R7510

Material: Graphite

Forming: Isostatically pressed

Application: High-temperature application

Material data of SIGRAFINE® R7510

Typical properties	Units	Test standards	Values*
Average grain size	µm	ISO 13320	10
Bulk density	g/cm ³	DIN IEC 60413/204	1.83
Open porosity	Vol. %	DIN 66133	10
Medium pore entrance diameter	µm	DIN 66133	1.8
Coefficient of permeability (ambient temperature)	cm ² /s	DIN 51935	0.06
Rockwell hardness HR _{5/100}		DIN IEC 60413/303	85
Resistivity	µΩm	DIN IEC 60413/402	13
Flexural strength	MPa	DIN IEC 60413/501	60
Compressive strength	MPa	DIN 51910	130
Dynamic modulus of elasticity	MPa	DIN 51915	11.5 x 10 ³
Thermal expansion (20 - 200 °C)	K ⁻¹	DIN 51909	4.2 x 10 ⁻⁶
Thermal conductivity (20 °C)	Wm ⁻¹ K ⁻¹	DIN 51908	105
Ash content	ppm	DIN 51903	200

* Typical average values of different rectangular and round block sizes. The actual individual block values might vary depending on dimension and format. For any engineering/design purposes please always contact our technical sales team.



Graphite Materials & Systems | SGL CARBON GmbH
 Sales Europe/Middle East/Africa | gms-europe@sglcarbon.com
 Sales Americas | gms-americas@sglcarbon.com
 Sales Asia/Pacific | gms-asia@sglcarbon.com
 www.fine-grain-graphite.com | www.sglcarbon.com

TDS R7510.01

12 2020/0 1NÄ Printed in Germany

®registered trademarks of SGL Carbon SE

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our "General Conditions of Sale".